

TH102 PET Chips Water Bottle Grade Technical Data Sheet

Tunhe TH102 PET resin with IV 0.80 is specially designed for water bottles.

Technical Specifications

Item	Unit	TH102 Water bottle Grade
Intrinsic Viscosity	dl/g	0.800±0.015
Color	L-Value	≥84
	B-Value	≤0
Melting Point	°C	245±2
Acetaldehyde Content	mg/kg	< 1.0
Density	g/cm ³	1.4±0.01
Terminal Carboxyl Group	mol/t	≤35
Ash Content	%	≤0.05
Powders	mg/kg	≤50
Moisture Content	%	≤0.2
Hundred-Granule-Weight	g	1.7±0.2
DEG Content	%	1.4±0.2

Applications

Chemate Technology Co.,Ltd

Add: NO.80 PUHUI ROAD,ZHENGZHOU CITY, HENAN PROVINCE, CHINA

URL: <https://www.chemategroup.com/tunhe-pet-chips/>

Email: sales@chemategroup.com

Phone: 0086-371-60921621

Whatsapp: +8618624832876



Precautions for use

1.Storage method: PET material is water-absorbent,therefore,it is recommended to store the entire package indoors.

2.Shelf life: PET products have no shelf life and can be used immediately after opening the package.It is recommended that the entire package be used within two years.

3.Use recommendations : PET pellets are sensitive to water at high temperatures. Excessive moisture may reduce the mechanical properties of the final product.Therefore, they need to be dried before use.The recommended drying conditions include a drying temperature of about 170℃drying dew point of -40℃and melting temperature of 280℃- 300℃

Chemate Technology Co.,Ltd

Add: NO.80 PUHUI ROAD,ZHENGZHOU CITY, HENAN PROVINCE, CHINA

URL: <https://www.chemategroup.com/tunhe-pet-chips/>

Email: sales@chemategroup.com

Phone: 0086-371-60921621

Whatsapp: +8618624832876