

PRODUCT DATA SHEET
POLYETHYLENE

Borstar® FB2230

ENHANCED POLYETHYLENE FOR HIGH PERFORMANCE FLEXIBLE PACKAGING

DESCRIPTION

Borstar®FB2230 is produced using the proprietary Borstar® bimodal technology resulting in easy extrusion with superior mechanical properties. Film made from the product exhibits excellent mechanical strength at normal as well as low temperature, good sealing properties and superior ESCR.

Borstar® FB2230 contains antioxidant.

CAS-No. 25087-34-7

APPLICATIONS

Mono layer & co-extrusion films
Lamination (incl. Stand up Pouches) Compression Packaging
Heavy duty shipping sacks Industrial Film
Form Fill Seal (FFS) Packaging
Agriculture Film (incl. Greenhouse Film) Shrink film
Geomembrane
Exclusive Carrier/Boutique bags Frozen Food
Impact modifier

KEY FEATURES

Easy process ability
Excellent impact strength – stiffness balance Good seal properties
Bubble stability
Excellent draw down
Toughness at low temperature Superior ESCR
Excellent printability

PHYSICAL PROPERTIES

Property	Typical Value*	Test Method
Density	923 kg/m ³	ASTM D 792
Melt Flow Rate (190°C/2.16kg)	0.25 g/10min	ASTM D1238
Melt Flow Rate (190°C/5.0kg)	1.0 g/10min	ASTM D1238
Melt Flow Rate (190°C/21.6kg)	22 g/10min	ASTM D1238
Melting Temperature	124 °C	ISO 11357/03
Vicat Softening Point A50 (10 N)	101 °C	ISO 306
ESCR – 10% Igepal – F 50%	>5000 Hours	ASTM D1693-B

FILM PROPERTIES1

Property**	Typical Value*	Test Method
Tensile Strength at Break (MD/TD)	50/40 MPa	ISO 527-3
Elongation at Break (MD/TD)	550/750 %	ISO 527-3
Tensile Strength at Yield (TD)	12 MPa	ISO 527-3
Tensile Modulus (1 % Secant) (MD/TD)	250/300 MPa	ASTM D 882
Coefficient of Friction	0.4	ASTM D 1894

CHEMATE TECHNOLOGY CO.,LTD

Tel: 0086-371-60921621

Whatsapp/Wechat: +8618624832876

Web: www.chemategroup.com

Add: NO.80 PUHUI ROAD,ZHENGZHOU CITY,
HENAN PROVINCE, CHINA

Gloss (60.)	10	ASTM D 2457
Dart Drop	600 g	ASTM D 1709/A
Tear Strength (MD/TD)	4/8 N	ASTM D 1922
Puncture Resistance, force	50 N	ASTM D 5748
Puncture Resistance, energy	3 J	ASTM D 5748

¹ Film properties: 40µm, BUR=3:1, FLH=4DD, Die gap 1.2mm

* Typical properties and data should not be used for specification work

** The film properties are dependent on extrusion conditions.

PROCESSING CONDITIONS

Borstar®FB2230 can be processed in most types of blown film equipment such as LDPE, LLDPE or HDPE extruders. The balance of draw down properties and bubble stability is superior to conventional LLDPE and LDPE. Thickness of 10 to >2000µm can be processed with good bubble stability. The product is well suited for co-extrusion.

Recommended extrusion temperature is 190 - 210°C. A die gap of 1.0 - 1.8 mm will give the best balance between extruder pressure and physical properties in the film. Wider die gap gives higher machine direction orientation.

Borstar®FB2230 provides excellent mechanical properties balance by optimizing film processing parameters like Blow up ratio (BUR) and Frost Line Height (FLH). Higher impact strength can be achieved by raising the FLH. High BUR (>2) also results in improved mechanical properties.

Recommended processing conditions:

Melt temperature	190 –210°C
Die gap	1.0 – 1.8 mm
FLH	2 - 4 DD
BUR	>2:1

FOOD CONTACT REGULATIONS

Borstar®FB2230 fulfils the food contact regulations in most countries. If required, contact your Borouge representative for a certificate.

STORAGE

This product should be stored in dry conditions at temperature bellow 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on physical properties of this product.

More information on storage can be found in Safety Information Sheet (SIS) for this product.

SAFETY

The product is not classified as a hazardous mixture.

Dust and fines from the product carry a risk of dust explosion. All equipment should be properly earthed. Inhalation of dust should be avoided as it may cause irritation of the respiratory system. Small amounts of fumes are generated during processing of the product. Proper ventilation is therefore required.

Please see our Safety Information Sheet (SIS) for details on various aspects of safety, recovery and disposal of the product, for more information contact your Borouge representative.

RECYCLING

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

CHEMATE TECHNOLOGY CO.,LTD

Tel: 0086-371-60921621

Whatsapp/Wechat: +8618624832876

Web: www.chemategroup.com

Add: NO.80 PUHUI ROAD,ZHENGZHOU CITY,
HENAN PROVINCE, CHINA